

Sales Catalog of HNK Telecommunication Products

Fiber Optic Cable

Multimode 62.5/125 OM1

This graded-index 62.5/125 μm multimode fiber has a 62.5 μm core diameter and a 125 μm cladding diameter. The fiber is designed for use at 850 nm and/or 1300 nm and is suitable for use in premises cabling applications, like Local Area Networks (including backbone, riser and horizontal) with video, data and/or voice services using LED, VCSEL and Fabry-Perot laser sources at 850 nm or 1300 nm.

This multimode fiber assures full compatibility with legacy systems, like Fast Ethernet, FDDL, ATM, Fiber Channel and 1Gb/s Ethernet. Because of the nature of the Plasma-activated Chemical Vapor Deposition(PVCD) manufacturing process, this fiber offers the highest bandwidth available in the market.

The fiber complies with or exceeds IEC 60793-2-10 type A1b Optical Fiber Specification, TIA/EIA-492AAAA-A detail specification.

Optical Characteristics for Multimode 62.5/125 μm (OM1)

CHARACTERISTIC	CONDITION	SPECIFIC VALUE	UNIT
Optical Characteristics			
	OM1		
Attenuation	850 nm	≤ 2.7	[dB/km]
	1300 nm	≤ 0.6	
Minimum Modal Bandwidth	850 nm	≥ 200	[MHz.km]
	1300 nm	≥ 600	
Link Length in Gigabit Ethernet	850 nm	≥ 500	[MHz.km]
	1300 nm	≥ 1000	
Numerical Aperture (NA)		0.275 ± 0.015	
Group Index of Refraction (Typical)	850 nm	1.496	
	1300 nm	1.491	
Zero Dispersion Wavelength, λ_0		1320~1365	[nm]
Zero Dispersion Slope, S_0	$1320\text{nm} \leq \lambda_0 \leq 1348\text{nm}$	≤ 0.11	[ps/(nm ² .km)]
	$1348\text{nm} \leq \lambda_0 \leq 1365\text{nm}$	$\leq 0.001(1458-\lambda_0)$	
Macro Bending Induced loss 100 Turns @ 37.5mm Radius	850 nm	≤ 0.50	[dB]
	1300 nm	≤ 0.50	
Geometrical Characteristics			
Core Diameter		62.5 ± 2.5	[μm]
Core Non-Circularity		≤ 5.0	[%]
Cladding Diameter		125.0 ± 1.0	[μm]
Cladding Non-Circularity		≤ 1.0	[%]
Coating Diameter		245 ± 7	[μm]
Coating/Cladding Concentricity Error		≤ 10.0	[μm]
Coating Non-Circularity		≤ 6.0	[%]
Core/Cladding Concentricity Error		≤ 1.5	[μm]
Delivery Length		Up to 8.8	[km/reel]
Environmental Characteristics			
Temperature Dependence (Induced Attenuation)	-60°C to +85°C	≤ 0.10	[dB/km]
Temperature Humidity Cycling (Induced Attenuation)	-10°C to +85°C, 4% to 98% RH	≤ 0.10	[dB/km]
Damp Heat Dependence (Induced Attenuation)	85°C and 85% RH, for 30days	≤ 0.10	[dB/km]
Water Soak Dependence (Induced Attenuation)	23°C, for 30days	≤ 0.10	[dB/km]
Dry Heat Aging	85°C, for 30days	≤ 0.10	[dB/km]
Back Scatter Characteristics			
	1300 nm		
Step (Mean of Bidirectional Measurement)		≤ 0.10	[dB]
Irregularities Over Fiber Length & Point Discontinuity		≤ 0.10	[dB]
Attenuation Uniformity		≤ 0.10	[dB/km]
Mechanical Characteristics			
Proof Test		≥ 9.0	[N]
		≥ 1.0	[%]
		≥ 100	[Kpsi]
Coating Strip Force	Typical Average Force	1.5	[N]
	Peak Force	≥ 1.3 & ≤ 8.9	[N]
Dynamic Stress Corrosion Susceptibility Parameter (N_d , Typical)		27	